AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. **(Currently Amended)** A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, comprising

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



(1)

wherein R^1 and R^2 each are a substituted or unsubstituted monovalent hydrocarbon radical, and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of $R^3{}_3SiO_{1/2}$ units and $SiO_{4/2}$ units in a molar ratio of $R^3{}_3SiO_{1/2}$ units to $SiO_{4/2}$ units of from 0.5 to 1.5, wherein R^3 is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of a silane or siloxane compound having a silicon atom-bonded alkoxy radical and an organic radical or atom selected from the group consisting of an alkenyl radical and a silicon atom-bonded hydrogen atom, a silane or siloxane compound having an epoxy radical and a silicon atom-bonded hydrogen atom, or a mixture thereof, and

(C) a crosslinking agent comprising (a) an organohydrogenpolysiloxane having at least two silicon atom-bonded hydrogen atoms in a molecule, in an amount to give 0.2 to 30 mol of silicon atom-bonded hydrogen atoms per mol of alkenyl radicals in components (A) and (B), and (b) a catalytic amount of a platinum base catalyst.

2-3. **(Canceled)**

4. **(Previously Presented)** A silicone adhesive film prepared by forming the adhesive of claim 1 into a film shape.

5. **(Previously Presented)** A silicone rubber adhesive film prepared by forming the adhesive of claim 1 into a film shape, followed by crosslinking and curing.

6. **(Currently Amended)** A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, said silicon adhesive comprising:

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



(1)

wherein ~~R1 and R2~~ R^1 and R^2 each are a substituted or unsubstituted monovalent hydrocarbon radical, and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of $R^3{}_3SiO_{1/2}$ units and $SiO_{4/2}$ units in a molar ratio of $R^3{}_3SiO_{1/2}$ units to $SiO_{4/2}$ units of from 0.5 to 1.5, wherein R^3 is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of a silane or siloxane compound having a silicon atom-bonded alkoxy radical and an alkenyl group or an epoxy radical, a silane or siloxane compound having an epoxy radical and a silicon atom-bonded hydrogen atom, or a mixture thereof, and

(C) (a) an organohydrogenpolysiloxane having at least two silicon atom-bonded hydrogen atoms in a molecule, in an amount to give 0.2 to 30 mol of silicon atom-bonded hydrogen atoms per mol of alkenyl radicals in components (A) and (B), and (b) a catalytic amount of a platinum base catalyst.

7. **(Previously Presented)** A silicone adhesive film prepared by forming the adhesive of claim 6 into a film shape.

8. **(Previously Presented)** A silicone rubber adhesive film prepared by forming the adhesive of claim 6 into a film shape, followed by crosslinking and curing.

9. **(Currently Amended)** A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, comprising:

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



(1)

wherein R^1 and R^2 each are a substituted or unsubstituted monovalent hydrocarbon radical, and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of $R^3_3SiO_{1/2}$ units and $SiO_{4/2}$ units in a molar ratio of $R^3_3SiO_{1/2}$ units to $SiO_{4/2}$ units of from 0.5 to 1.5, wherein R^3 is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of a silane or siloxane compound having a silicon atom-bonded alkoxy radical and an organic radical or atom selected from the group consisting of an ~~alkenyl radical, an~~ epoxy radical and a silicon atom-bonded hydrogen atom, a silane or siloxane compound having an epoxy radical and a silicon atom-bonded hydrogen atom, or a mixture thereof, and

(C) a crosslinking agent in the form of an organic peroxide.

10. **(Currently Amended)** The silicone adhesive of claim 9, wherein component (B) is a siloxane compound having a silicon atom-bonded alkoxy radical and an organic radical or atom selected from the group consisting of an ~~alkenyl radical, an~~ epoxy radical and a silicon atom-

bonded hydrogen atom, a silane or siloxane compound having an epoxy radical and a silicon atom-bonded hydrogen atom, or a mixture thereof.

11. **(Currently Amended)** A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, comprising:

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



(1)

wherein R^1 and R^2 each are a substituted or unsubstituted monovalent hydrocarbon radical, and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of $R^3{}_3SiO_{1/2}$ units and $SiO_{4/2}$ units in a molar ratio of $R^3{}_3SiO_{1/2}$ units to $SiO_{4/2}$ units of from 0.5 to 1.5, wherein R^3 is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of a silane or siloxane compound selected from the group consisting of the following compounds:

~~acryloxypropyltrimethoxysilane,~~

~~acryloxypropylmethyldimethoxysilane,~~

~~acryloxypropyltriethoxysilane,~~

~~methacryloxypropyltrimethoxysilane,~~

~~methacryloxypropylmethyldimethoxysilane,~~

~~methacryloxypropyltriethoxysilane,~~

glycidoxypropyltrimethoxysilane,

glycidoxypropyltriethoxysilane,



,



,



,



,



,



,



wherein p and r each are an integer of 0 to 50, q, s and t each are an integer of 1 to 50,



, and



, and

(C) a crosslinking agent in the form of an organic peroxide.

12. **(Previously Presented)** A silicone adhesive film prepared by forming the adhesive of claim 9 into a film shape.

13. **(Previously Presented)** A silicone rubber adhesive film prepared by forming the adhesive of claim 9 into a film shape, followed by crosslinking and curing.

14. **(Previously Presented)** A silicone adhesive film prepared by forming the adhesive of claim 11 into a film shape.

15. **(Previously Presented)** A silicone rubber adhesive film prepared by forming the adhesive of claim 11 into a film shape, followed by crosslinking and curing.

16. (**New**) A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, comprising:

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



(1)

wherein R^1 and R^2 each are a substituted or unsubstituted monovalent hydrocarbon radical, and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl

radicals in a molecule and consisting essentially of $R^3_3SiO_{1/2}$ units and $SiO_{4/2}$ units in a molar ratio of $R^3_3SiO_{1/2}$ units to $SiO_{4/2}$ units of from 0.5 to 1.5, wherein R^3 is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of an organosilane or organosiloxane-modified isocyanurate compound, and

(C) a crosslinking agent.

17. (**New**) The silicone adhesive of claim 16, wherein component (B) is



or



18. (**New**) The silicone adhesive of claim 16, wherein component (C) is an organo peroxide, or (a) an organohydrogenpolysiloxane having at least two silicon atom-bonded hydrogen atoms in a molecule, in an amount to give 0.2 to 30 mol of silicon atom-bonded

hydrogen atoms per mol of alkenyl radicals in components (A) and (B), and (b) a catalytic amount of a platinum base catalyst.

19. (**New**) A silicone rubber adhesive film prepared by forming the adhesive of claim 16 into a film shape, followed by crosslinking and curing said adhesive.